

# Experimental Analysis on Vulnerability of RCC Members Due to Floods

Aarthi Nagarajan<sup>1</sup>, Adharsh. G<sup>2</sup>, Tamil Chirpi<sup>3</sup>

<sup>1,2</sup>Assistant Professor, <sup>3</sup>U.G Scholar,

<sup>1,2,3</sup>Department of Civil Engineering, S. A. Engineering College, Chennai, Tamil Nadu, India

## ABSTRACT

This project gives the remedial measures for the buildings that are severely affected by floods. The buildings in the flood-prone areas of Chennai city are mapped using ArcGIS. Mapping of these areas helps to make immediate strategies on those areas during a flood. Various techniques are incorporated to reduce the vulnerability of the building. Crystalline admixture has been used to turn the normal ordinary Portland cement to hydrophobic cement which makes it highly water repellent. Epoxy resin is applied as a coating to the reinforced bars to make it corrosion-resistant and helps it to fight against sulphate attack. These techniques are also applicable during the construction of coastal buildings with very low vulnerability. Using of these techniques in buildings helps the structure to gain more durability and sustainability especially during the time of flood.

**KEYWORDS:** Hydrophobic concrete, Arc GIS, Corrosion resistance

**How to cite this paper:** Aarthi Nagarajan | Adharsh. G | Tamil Chirpi "Experimental Analysis on Vulnerability of RCC Members Due to Floods" Published in International Journal of Trend in Scientific Research and Development (ijtsrd), ISSN: 2456-6470, Volume-4 | Issue-3, April 2020, pp.855-858, URL: [www.ijtsrd.com/papers/ijtsrd30697.pdf](http://www.ijtsrd.com/papers/ijtsrd30697.pdf)



IJTSRD30697

Copyright © 2020 by author(s) and International Journal of Trend in Scientific Research and Development Journal. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (CC BY 4.0) (<http://creativecommons.org/licenses/by/4.0/>)





## 1. INTRODUCTION


Due to the flood, the vulnerability of buildings in flood-prone areas is extremely high. Because of this, the durability and sustainability of the buildings are reduced greatly. To stop this, we are incorporating techniques like epoxy resin and hydrophobic cement which decreases the vulnerability of the buildings. Application of epoxy resin to reinforcement bars helps the bar to withstand sulphate and corrosion attack. During the time of flood, the stagnant water around the buildings infiltrates into the concrete and affects the bars to reduce this, epoxy resin is used. Hydrophobic cement is majorly used in the construction of water structures like dams, spillways, and etc. Due to the unavailability of hydrophobic cement, crystalline powder is added to cement which helps the normal OPC cement to turn as hydrophobic cement which is extremely water repellent.

## 2. MAPPING OF FLOOD PRONE AREAS USING ArcGIS

The mapping of flood-prone areas in Chennai city is done, for incorporating various flood mitigation techniques to save the lives of people and to reduce the vulnerability of the buildings. Also, the affected areas of Chennai city during the December 2, 2015, is mapped and shown in the below figures.



**Fig 1 Possible flood-prone areas of Chennai**



**Fig 2 Affected areas of Chennai during December flood**

### 3. HYDROPHOBIC CONCRETE

The hydrophobic concrete is produced based on the technology used in Crystalline waterproofing is manufactured in the form of a dry powder compound which comprises of Portland cement, very fine treated silica sand, and proprietary chemicals. It's applied as a coating material, admixture and dry shake. Crystalline Waterproofing Technology enhances the durability of concrete structures by pore-blocking mechanism, where in the pores, capillaries and micro-cracks in the concrete are blocked with a non-soluble, crystalline formation. The crystalline waterproofing admixture can be supplemented to concrete at the time of batching as well as at the site immediately before pouring of the concrete which then forms part of concrete and helps in making it dense and watertight.

### 4. EXPERIMENTAL TESTS

Since the study mainly aims the study of corrosive properties of the hydrophobic concrete designed, only the basic compressive test is done for the primary achievements. Hence 18 cubes of M20 grade concrete specimens dimensions 150mm ×150mm were casted. 9 cubes were casted as conventional concrete (Control concrete) and 9 cubes were casted as un-conventional concrete (crystalline admixture mixed concrete) and to study the corrosive properties of hydrophobic concrete half-cell potential meter test was conducted for four cylinders of 150 mm diameter cylinders, 2 cylinders for conventional and 2 cylinders for un-conventional concrete

#### 4.1. COMPRESSIVE STRENGTH TEST

Compressive strength test was conducted for 7, 14 and 28 days for both conventional and un-conventional concrete and results were obtained as follows, an average of 3 cubes were tested for one particular day test

**Table 1 - Average compressive strength test of conventional concrete cubes**

Days	7 <sup>th</sup> day	14 <sup>th</sup> day	28 <sup>th</sup> day
Average compressive strength	13.17 N/mm <sup>2</sup>	15.83 N/mm <sup>2</sup>	23.49 N/mm <sup>2</sup>

**Table 2 - Average compressive strength test of un-conventional concrete cubes**

Days	7 <sup>th</sup> day	14 <sup>th</sup> day	28 <sup>th</sup> day
Average compressive strength	21.97 N/mm <sup>2</sup>	26.33 N/mm <sup>2</sup>	27.2 N/mm <sup>2</sup>



#### Fig1. Compressive strength test of concrete specimen

#### 4.2. HALF CELL POTENTIOMETER TEST

The method of half-cell potential measurements normally involves measuring the potential of an embedded reinforcing bar relative to a reference half-cell placed on the concrete surface. The half-cell is usually a copper/copper sulphate or silver/silver chloride cell but other combinations are used. The concrete functions as an electrolyte and the risk of corrosion of the reinforcement in the immediate region of the test location may be related empirically to the measured potential difference. In some circumstances, useful measurements can be obtained between two half-cells on the concrete surface. ASTM C876 - 91 gives a Standard Test Method for Half-Cell Potentials of Uncoated Reinforcing Steel in Concrete.

The instrument measures the potential and the electrical resistance between the reinforcement and the surface to evaluate the corrosion activity as well as the actual condition of the cover layer during testing. The electrical activity of the steel reinforcement and the concrete leads them to be considered as one half of weak battery cell with the steel acting as one electrode and the concrete as the electrolyte. The electrical potential of a point on the surface of steel reinforcing bar can be measured comparing its potential with that of copper – copper sulphate reference electrode on the surface. Practically this is achieved by connecting a wire from one terminal of a voltmeter to the reinforcement and another wire to the copper sulphate reference electrode.

**Table 3 – Corrosion test results**

Trial number	Specimen details	Readings	Probability of corrosion
1	Conventional cylinder	-384	High probability of corrosion
2	Crystalline Admixture and Epoxy resin in reinforcement	-281	Uncertainty of corrosion

Less than 200 - 10% of corrosion  
 Between 200 to 350 - 50% of corrosion (Uncertain)  
 Above 350 - 90% of corrosion



**Fig 3. Half-Cell Potentiometer Test Equipment**



Fig.4 Test specimen

## 5. RESULTS AND DISCUSSION




Fig 5. Comparison of Compressive strength test between Conventional and Un-Conventional test




Fig 6. Comparison of Corrosion test between Conventional and Un-Conventional test

## 6. CONCLUSION

Thus the remedies for reducing the vulnerability of buildings in flood prone areas have been discussed and it has been proved that, using of crystalline admixture in Cement makes it has water repellent and increased the compressive strength of concrete considerably. And the coating of epoxy resin in reinforcement bars helps it to withstand the sulphate and corrosion attack. So these techniques can be incorporated in flood and coastal areas to increase the sustainability and durability of buildings.

## 7. REFERENCES

- [1] Mazen.J.Al-Kheetan, Mujib M.Rahman, Denis A.Chamberlain – “Development of hydrophobic concrete by adding dual-crystalline admixture at mixing stage”- Structural concrete, Volume 1, issue 8, February 2018.
- [2] Jiri Pazderka, Eva Hajkova – “Crystalline admixture and their effects on selected properties of concrete” – Acta Polytechnica, Volume 56, issue 4, 2016.
- [3] Navaratnarajah Sathiparan – “An assessment of

- building vulnerability to a tsunami in the Galle coastal area, Sri Lanka" – Journal of building engineering, Volume 27, September 2019.
- [4] Pavel Reiterman and Jiri Pazderka – "Crystalline Coating and Its Influence on the Water Transport in Concrete" – Advances in Civil engineering, Volume 2016, July 2016.
- [5] Usman Hasan Jalali, Sher Afgan- "Analysis of Integral Crystalline Waterproofing Technology for Concrete"- International Research Journal of Engineering and technology, Volume 5, issue 10, October 2018.
- [6] Sandhya kiran, Vijay Kumar – "Flood mapping analysis of Chennai city flood"- International journal of recent trends in engineering and research, Volume 3, issue 7, July 2017.
- [7] D.Thiyagarajan, V. Vasanth Kumar, K. Mohan Prabhu, R. Thamizhselvan – "Flood modelling of Adyar basin" - International Research Journal of Engineering and technology, Volume 7, issue 3, 2018.
- [8] Xinying xie, Xuan zhang, Yujie jin, Wei Tian – "Research Progress of Epoxy Resin Concrete" – Earth and Environmental science, Volume 186, 2018.
- [9] Yongxing Zhang, Min Zhao, Jiaoxia Zhang, Qian Shao, Jianfeng Li, Hang Li, Bo Lin, Meiyang Yu, Shougang Chen, Zhanhu Guo – "Excellent corrosion protection performance of epoxy composite coatings filled with silane functionalized silicon nitride" – Journal of polymer research, Volume 25, issue 130, May 2018.

